DuPont Packaging & Industrial Polymers



DuPont[™] Elvaloy® AC 1330 Elvaloy® AC resins Product Data Sheet

escription			
Product Description	Elvaloy® AC 1330 is a copolymer of ethylene and methyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.		
estrictions			
Material Status	Commercial: Active		
pical Characteristics			
Composition	30 % By Weight Methyl Acrylate comonomer content		
Features	Contains Slip additive.		
vpical Properties			
Physical	Nominal Values	Test Method(s)	
* Density ()	0.95 g/cm ³	ASTM D792 ISO 1183	
 Melt Flow Rate (190°C/2.16kg) 	3 g/10 min	ASTM D1238 IS0 1133	
Thermal	Nominal Values	Test Method(s)	
* Melting Point (DSC)	85°C (185°F)	ASTM D3418 ISO 314	
rocessing Information			
General			
* Maximum Processing Temperature	310°C (590°F)		
General Processing Information	Elvaloy® AC 1330 is normally processed at melt temperatures ranging from 160°C 235°C (320°F - 455°F) in blown film or cast film equipment. A typical blown film extruder temperature profile is given below. Actual processing temperatures will be determined by either the specific equipment or one of the other polymers in a coextrusion. Elvaloy® AC 1330 can also be used in cast extrusions and coextrusions. It is easily processed on standard equipment used for low density polyethylene.		
Blown Film Processing	Nominal Values		
Blown Film Processing Information	A suggested extrusion set ter	mperature profile is shown below.	
Feed Zone	135°C (275°F)		
Feed Zone Second Zone	135°C (275°F) 160°C (320°F)		

Fifth Zone	185°C (365°F)	
Adapter Zone	185°C (365°F)	
Die Zone	185°C (365°F)	
FDA Status Information	Elvaloy® AC 1330 Acrylate Copolymer Resin complies with Food & Drug Administration Regulation 21 CFR 175.105 Adhesives. This Regulation describes adhesives that may be used as components of articles intended for use in packaging, transporting, or holding food, subject to the limitations and requirements therein.	
	Elvaloy® AC 1330 Acrylate Copolymer Resin complies with Food & Drug Administration Regulation 21 CFR 176.180 Components of paper and paperboard in contact with dry food, subject to the limitations and requirements therein. This Regulation describes substances that may be used as components of the uncoated and coated food-contact surface of paper and paperboard in contact with dry food (Food Type VIII, identified in 21 CFR 176.170(c) Table 1).	
	The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by DuPont and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, DuPont cannot guarantee or warrant such certifications or information and assumes no liability for their use.	
Regulatory Information	For information on regulatory compliance outside of the U.S., consult your local DuPont representative.	
Safety & Handling	For information on appropriate Handling & Storage of this polymeric resin, please refer to the Material Safety Data Sheet.	
	A Product Safety Bulletin, Material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your DuPont Packaging and Industrial Polymers representative.	

Read and Understand the Material Safety Data Sheet (MSDS) before using this product

Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company Chestnut Run Plaza – Bldg. 730 974 Centre Road Wilmington, Delaware 19805 U.S.A. Toll-Free (USA): 1-800-628-6208 Telephone: 1-302-774-1000 Fax: 1-302-355-4013

DuPont do Brasil, S.A. Alameda Itapecuru, 506 06454-080 Barueri, SP Brasil Telephone: +55 11 4166 8000

Asia Pacific

DuPont China Holding Co., Ltd. Shanghai Branch 399 Keyuan Road, Bldg. 11 Zhangjiang Hi-Tech Park Pudong New District, Shanghai P.R. China (Postcode: 201203) Telephone +86 21 3862 2888 Fax +86-21-3862-2889

Europe / Middle East / Africa

DuPont de Nemours Int'1. S.A. 2,Chemin du Pavillon Box 50 CH-1218 Le Grand Saconnex Geneva, Switzerland Telephone +41 22 717 51 11 Fax +41 22 717 55 00

Fax: +55 11 4166 8736

http://elvaloy.dupont.com

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medicalk applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPontTM, The miracles of scienceTM, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

This data sheet is effective as of 08/08/2010 12:30:09 PM and supersedes all previous versions.